Memphis Backdrops

ST-2101T/ST-2101D

Soyang's comprehensive range: PVC-Free. Supported by full industry chain. Compatible with various printing methods.

BRIEF DESCRIPTION

- 100% warp-knitted polyester fabric with white surface and black back
- Excellent opacity fully keeps its advantage as backdrops
- Slight stretch and soft hand feel feature makes it widely used as frame, stretch display, light curl geometric, grandformat, etc

FEATURES



ΑΤΕΧ

INK PRINTABILITY



DYE paper

MATERIAL DETAILS

| PROPERTIES | TEST METHOD | METRIC | IMPERIAL |
|-----------------------------------|--|-------------------------------|--------------|
| Total Weight | DIN EN ISO 2286-2, ASTM D751 | 320 g/sq.m | 9.4 oz/sq.yd |
| Base Fabric | DIN 60001, ASTM D7641 | 100%Polyester | |
| Weave Method | N/A | Warp-knitted | |
| Shrinkage | 210 °C, 30s | ≤2% | |
| Shielding Rate | ANSI PH2.19, ISO 5/2 | 99% | |
| Elasticity | Length*Width=200*50mm, Speed=100mm/min, Tension=20N | Warp: 4% Weft: 1% | |
| Flame Resistance | DIN 4102-1-B1, NFPA 701 Test1 | DIN 4102-1-B1, NFPA 701 Test1 | |
| Recommend Fixation Temperature | N/A | 190°C, 30s | |
| Width Available | DIN EN ISO 3759, ASTMD751-2006 | Max 320cm | 126" |
| Standard Length | DIN EN ISO 3759, ASTMD751-2006 | 50m | 55yds |

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.





