Poseidon Backdrops



ST-210T/ST-210D

Soyang's comprehensive range: PVC-Free. Supported by full industry chain. Compatible with various printing methods.

BRIEF DESCRIPTION

- 100% warp-knitted polyester fabric with white surface and grey back
- Great opacity fully keeps its advantage as backdrops wall
- Slight stretch and soft hand feel feature makes it widely used as frame, backdrops, stretch display, light curl geometric, grandformat, etc

FEATURES









INK PRINTABILITY





MATERIAL DETAILS

TEST METHOD	METRIC	IMPERIAL
DIN EN ISO 2286-2, ASTM D751	280 g/sq.m	8.3 oz/sq.yd
DIN 60001, ASTM D7641	100%Polyester	
N/A	Warp-knitted	
210 ℃, 30s	≤2%	
ANSI PH2.19, ISO 5/2	93%	
Length*Width=200*50mm, Speed=100mm/min, Tension=20N	Warp: 7%	Weft: 8%
DIN 4102-1-B1, NFPA 701 Test1	DIN 4102-1-B1, NFPA 701 Test1	
N/A	190℃, 30s	
DIN EN ISO 3759, ASTMD751-2006	Max 320cm	126"
DIN EN ISO 3759, ASTMD751-2006	50m	55yds
	DIN EN ISO 2286-2, ASTM D751 DIN 60001, ASTM D7641 N/A 210 ℃, 30s ANSI PH2.19, ISO 5/2 Length*Width=200*50mm, Speed=100mm/min, Tension=20N DIN 4102-1-B1, NFPA 701 Test1 N/A DIN EN ISO 3759, ASTMD751-2006	DIN EN ISO 2286-2, ASTM D751 280 g/sq.m DIN 60001, ASTM D7641 100%Po N/A Warp-k 210 °C, 30s ≤2° ANSI PH2.19, ISO 5/2 93° Length*Width=200*50mm, Warp: 7% Speed=100mm/min, Tension=20N DIN 4102-1-B1, NFPA 701 Test1 DIN 4102-1-B1, I N/A 190°C DIN EN ISO 3759, ASTMD751-2006 Max 320cm

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.







